

## Name

BTL™ 16N

## Description

Woven fabric incorporating exclusive coatings designed to improve toughness and abrasion resistance.

## Fabric specifications

Weave: Woven black HDPE scrim  
Coating: LDPE, avg. 59 g/m<sup>2</sup>/side  
Colour: black  
Weight: 244 g/m<sup>2</sup> ± 10%

## Roll specifications

Core: 10.16 cm inner diameter  
Width: max. 366 cm (-0, +1.3)  
Length: min. 229 m/roll  
max. 914 m/roll

*These values are typical data and are not intended as limiting specifications.*

## Performance properties

*The following data are typical values based on ASTM standard tests. These data should not be considered specification.*

*MD: machine direction, TD: transverse direction*

<b>Thickness</b> ASTM D1777	Nominal 0.40 mm ± 10%
<b>Grab Tensile</b> ASTM D7004	MD 932 N / TD 840 N
<b>Strip Tensile</b> ASTM D7003	MD 1199 N/5cm / TD 1154 N/5cm
<b>Tongue Tear (large scale)</b> ASTM D5884	MD 266 N / TD 266 N
<b>Mullen Burst</b> ASTM D751	2583 kPa
<b>MVTR</b> ASTM E96 Proc. BW	0.40 g/m <sup>2</sup> ·24hr (0.06 perms)
<b>Hydraulic Conductivity</b> (Permeability) Calculated from MVTR	1.27 x 10 <sup>-12</sup> cm/s
<b>Hydrostatic Resistance</b> ASTM D751	672 kPa
<b>Puncture Resistance</b> ASTM D4833	505 N
<b>Carbon Black Content</b> ASTM D4218	6.0%
<b>Dimensional Stability</b> ASTM D1204	MD -3.6% / TD -3.4%
<b>Low Temperature Flex</b> ASTM D2136	MD & TD: Pass @ -40°C
<b>Seam Strength (shear), min.</b> ASTM D7747	Seam shear should be >80% of the strip tensile of the base fabric
<b>Seam Strength (peel), min.</b> ASTM D413	27 N/5cm
<b>Accelerated UV Weathering<sup>1</sup></b> ASTM G151 ASTM G154	>90% strength retention after 2000 hrs exposure @ 0.77 W/m <sup>2</sup> /nm, or 1200 hrs exposure @ 1.35 W/m <sup>2</sup> /nm

<sup>1</sup>: Q.U.V [A-340 Lamps]; 8 hrs UV @ 60°C; 4 hrs condensation @ 50°C

Statements and information contained in this data sheet serve as general guidance and made public based on currently available knowledge. Content is subject to change. In all cases, it is the sole responsibility of the end user and / or designer to ensure that a specific product is suitable for a specific purpose under particular circumstances, and the availability of the latest version of the data sheet.

**Please contact the distributor - Creatiger Kft. - for warranty details.**



Creatiger Kft.  
www.creatiger.hu | info@creatiger.hu  
Effective: 01. 04. 2014.